

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-207134

(43)Date of publication of application : 08.08.1995

(51)Int.Cl.

C08L 69/00  
C08K 5/54

(21)Application number : 06-004069

(71)Applicant : MITSUBISHI CHEM CORP

(22)Date of filing : 19.01.1994

(72)Inventor : KAWA MANABU

## (54) AROMATIC POLYCARBONATE RESIN COMPOSITION

## (57)Abstract:

PURPOSE: To obtain an aromatic polycarbonate resin composition containing an intercalation compound containing a specific laminar silicate as a host and an organic onium ion as a guest, respectively, in a specific amount as an inorganic ash content and excellent in strength, stiffness, toughness, ductility, surface appearance of molding, melt fluidity and dimensional accuracy.

CONSTITUTION: This composition contains an intercalation compound containing a laminar silicate having  $\geq 30$ mm equivalent/100g, preferably  $\geq 70$ mm equivalent/100g of cation exchange capacity as a host, and an organic onium ion (preferably a quaternary onium ion having preferably  $\geq$  a 12C alkyl group, especially trimethyloctadecylammonium ion) as a guest, respectively, in an amount of 0.1-10wt.%, preferably 0.3-4wt.% as an inorganic ash content.

## LEGAL STATUS

[Date of request for examination] 20.12.2000

[Date of sending the examiner's decision of rejection] 28.05.2002

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]